

lucitelux Light Guide Panel LXN 875 Technical Bulletin

	Test Procedure	Method		Value	Unit
Optical	Luminous Transmittance Haze Refractive Index	ASTM D1003 ASTM D1003 ASTM D542	JIS K 7361-1 JIS K 7136 JIS K 7142	>90 4 1.49	% % -
Mechanical	Tensile Strength(rupture) Elongation @ rupture Flexural Strength (rupture) Modulus (elasticity) Rockwell hardness Izod (impact) Charpy (impact)	ASTM D638 ASTM D638 ASTM D790 ASTM D790 ASTM D785 ASTM D256 ASTM D6110	JIS K 7162 JIS K 7162 JIS K 7171 JIS K 7171 JIS K 7002-2 JIS K 7110 JIS K 7111	75 4.5 120 3.2 100 2.0	MPa % MPa GPa M scale kJ/m² kJ/m²
Thermal	Specific Heat Deflection Temperature under load Coefficient of thermal expansion	- ASTM D648 ASTM D696	JIS K 7123 JIS K 7191-2 JIS K 7197	1.5 96 7.E-05	J/g°C °C cm/cm/deg
Electrical	Surface Resistivity	ASTM D257	JIS K 6911	>1E16	Ω/sq
Miscellaneous	Abrasion/Mar resistance (Tabor -100 cycles) Specific gravity Water Absorption Flammability Intrinsic Viscosity	ASTM D4060 ASTM D792 ASTM D570 UL 94	JIS K 7204 JIS K 7112 JIS K 7209 - JIS K 7367-1	40 1.19 0.3 HB cross- linking	% haze g/cm³ % l/g

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should perform their own tests to determine the suitability of these products for their own particular purposes. Statements made herein should, therefore, not be construed as representations or warranties. The responsibilities of Lucite International, Inc. for claims arising out of breach of warranty, negligence, strict liability, or otherwise is limited to the purchase price of the material. Statements made herein concerning the use of the products or formulations described herein are not to be construed as granting a license to operate under any patent of Lucite International, Inc. or another, or as recommending the infringement of any patent of Lucite International, Inc. or another, and no liability for infringement arising out of any such use is assumed

rev. 1-19-16

